

Indorama Eleme Petrochemicals Limited

TECHNICAL DATA SHEET

INDORAMA – BOPP

NGP034S

PP HOMOPOLYMER GRADE FOR BOPP FILMS

NGP034S Homopolymer Polypropylene Resin manufactured by IEPL using Spheripol process of Basell, Italy. It is recommended grade for Bi-axially Oriented Polypropylene (BOPP) films, which can be used in food packaging, cigarette & textile overwraps, lamination and synthetic paper etc.

TYPICAL CHARACTERISTICS:

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE
Melt Flow Index (230°C / 2.16 Kg)	ASTM D 1238	gm/10 min.	3.4
Density at 23°C	ASTM D 1505	gm/cm ³	0.9
Tensile Strength at Yield	ASTM D 638	Mpa	30
Elongation at Yield	ASTM D 638	%	10
Flexural Modulus	ASTM D 790	Mpa	1350
Notched Izod Impact @ 23°C	ASTM D 256	J/m	40
Heat Deflection Temp. 0.46 N/mm ²	ASTM D 648	°C	104

Above values are not to be construed as specifications.

PRODUCT BENEFITS	APPLICATIONS
<ul style="list-style-type: none"> • High Rigidity • High tensile strength • Good retention of corona treatment • Low odor level • Excellent gloss and clarity • Good processability 	<ul style="list-style-type: none"> • Packaging film for food • Overwraps for cigarette & textile • Lamination • Synthetic paper

PACKAGING: NGP034S is available in natural colour, pellets form in 25 Kg bags.

FOOD CONTACT APPLICATIONS: NGP034S grade and the additives incorporated in it comply with the US FDA : CFR title 21, 177.1520 and EU regulation 10/2011 for food contact application when used unmodified and processed according to good manufacturing practices. Please contact us for details information and/or compliance certification documents.

Our commitment to Quality, Health, Safety and Environment has been evident from the fact that IEPL is certified with all three ISO Standards ISO 9001, 14001 and OHSAS 18001.

Indorama Eleme Petrochemicals Limited

TECHNICAL DATA SHEET

SAFETY

The Material Safety Data Sheet (MSDS) contains information regarding health, safety and waste considerations for all IEPL Polypropylene Homopolymer grades. We urge each customer or recipient of MSDS to study it carefully to become aware of and understand the hazards associated with the product. The customer should consider consulting reference works or individuals who are experts in ventilation, toxicology or fire prevention, as necessary or appropriate to use and understand the data contained in the MSDS.

STORAGE

The material is packed in 25 kg bags protecting it from contamination. Storage times of natural materials longer than 6 months may have a negative influence on the quality of the final product. It is generally recommended to convert all material latest within 6 months of production. The material is subjected to degradation by ultra-violet radiation or by high storage temperatures. Therefore the material must be protected from direct sunlight, temperatures above 40°C and high atmospheric humidity during storage. Further unfavorable storage conditions are large fluctuations in ambient temperature and high atmospheric humidity. These conditions may lead to moisture condensing inside the packaging. Under these circumstances, it is recommended to dry the material before use. After a storage period of more than 3 months drying of such material is recommended as standard practice.

DISCLAIMER

The data, information and suggestions given herein are purely as a guide. IEPL undertakes no responsibility either for the results derived from their adoption or for possible positions in apparent contrast with existing patent rights. In view of the many factors that may affect processing and application, these data do not reveal the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or on the basis of the information in this publication.

OFFICES:

Lagos	Port Harcourt	Kano
12th Floor, Zenon House, Ajose Adeogun Street, Victoria Island, Lagos	IEPL Complex, PMB 5151, Port Harcourt, Rivers State	No. 6, Niger Street, Dakata Kano State
E-mail: lgsales@indorama.com.ng	E-mail: phcsales@indorama.com.ng	E-mail: kanosales@indorama.com.ng
Exports	Customer Services	
E-mail: export@indorama.com.ng	E-mail: techsupport@indorama.com.ng	

www.indoramaeleme.com

Our commitment to Quality, Health, Safety and Environment has been evident from the fact that IEPL is certified with all three ISO Standards ISO 9001, 14001 and OHSAS 18001.