

**TECHNICAL DATA SHEET**

**INDORAMA- PPCP**

**NGC120I**

**POLYPROPYLENE COPOLYMER FOR INJECTION MOULDING**

NGC120I is a polypropylene impact copolymer resin manufactured by IEPL using bulk polymerization technique, “SPHERIPOL” Technology by Basell. The grade is recommended for use in injection moulding process where good impact strength is required. The resin contains Nucleating agent. It is an ideal material to use in making furniture, Automotive parts, etc.

**TYPICAL CHARACTERISTICS:**

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE
Melt Flow Index (230°C / 2.16 Kg )	ASTM D 1238	gm/10 min.	12.0
Density at 23°C	ASTM D 792	gm/cm <sup>3</sup>	0.9
Tensile Strength at Yield	ASTM D 638	Mpa	25
Elongation at Yield	ASTM D 638	%	12
Flexural Modulus	ASTM D 790	Mpa	1300
Notched Izod Impact @ 23°C	ASTM D 256	J/m	100
Vicat Softening Point	ASTM D 1525	°C	151
Rockwell Hardness	ASTM D 785	R Scale	105
Heat Deflection Temp. 0.46 N/mm <sup>2</sup>	ASTM D 648	°C	95

Note- Above values are not to be construed as specifications.

-Mechanical Properties are on Injection Moulded Specimen

PRODUCT BENEFITS	APPLICATIONS
<ul style="list-style-type: none"> <li>• High stiffness</li> <li>• Good impact strength</li> <li>• Very good processibility</li> <li>• Good dimensional stability</li> <li>• Low static charges</li> </ul>	<ul style="list-style-type: none"> <li>• Garden furniture</li> <li>• Industrial products</li> <li>• Automotive components</li> <li>• Housewares</li> <li>• Sanitary wares</li> <li>• Toys</li> </ul>

**PACKAGING:** NGC120I is available in natural colour, pellets form in 25 Kg bags made of woven fabric.

**FOOD CONTACT APPLICATIONS:** This grade meets with the requirements of FDA: CFR title 21, 177.1520 and EU regulation 10/2011 for food contact application when used unmodified and processed according to good manufacturing practices.

IEPL’s commitment to Quality, Health, Safety and Environment is evident from the fact that it is certified with all three ISO Standards ISO 9001, 14001 and 45001.

**SAFETY**

The Material Safety Data Sheet (MSDS) contains information regarding health, safety, and waste considerations for all IEPL Polypropylene Impact Copolymer grades. We urge each customer or recipient to study the MSDS carefully to become aware of and understand the hazards associated with the product.

**STORAGE**

Material bags should be stored in dry and closed conditions to avoid the moisture contamination and at temperature below 40°C. It should be protected from direct sunlight/UV light to prevent the material degradation. It is generally recommended to convert all material latest within 6 months of production. After a storage period of more than 3 months drying of material is recommended as standard practice.

**DISCLAIMER**

The data, information and suggestions given herein are purely as a guide. IEPL undertakes no responsibility either for the results derived from their adoption or for possible positions in apparent contrast with existing patent rights. In view of the many factors that may affect processing and application, these data do not reveal the receiver of this information from the responsibility of carrying out their own tests and experiments; neither do they imply any legally binding assurance of certain properties or of suitability for a specific purpose of the products made with or based on the information in this publication.

**OFFICES:**

<b>Lagos</b>	<b>Port Harcourt</b>	<b>Kano</b>
5 <sup>th</sup> Floor, Pactum Towers,	Indorama Complex,	Opp Talamiz Oil Mill (TOM), Beside UNIFOAM Factory
Plot 1220, Ahmadu Bello Way,	East West Expressway, Eleme,	Gunduwawa Area, Along Kano Hadejia Road
Victoria Island, Lagos, Nigeria	Port Harcourt, River State, Nigeria	Gezawa LGA Kano, Kano State, Nigeria
E-mail: <a href="mailto:lgsales@ng.indorama.com">lgsales@ng.indorama.com</a>	E-mail: <a href="mailto:phcsales@ng.indorama.com">phcsales@ng.indorama.com</a>	E-mail: <a href="mailto:kanosales@ng.indorama.com">kanosales@ng.indorama.com</a>

<b>Exports</b>		<b>Customer Services</b>
E-mail: <a href="mailto:iplexports@ng.indorama.com">iplexports@ng.indorama.com</a>		E-mail: <a href="mailto:customercare@ng.indorama.com">customercare@ng.indorama.com</a>

**[www.indoramaeleme.com](http://www.indoramaeleme.com)**